

## FILARC PZ6500

A copper coated, manganese-silicon alloyed rod for GTAW of all general engineering and structural steels with a minimum yield strength of max 420 MPa. The rod is usually welded with pure argon (I1) as the shielding gas.

Specifications	
<b>Classifications</b>	EN ISO 636-A : W 42 3 3Si1 EN ISO 636-A : W 3Si1 SFA/AWS A5.18 : ER70S-6
<b>Approvals</b>	CE : EN 13479 UKCA : EN 13479 VdTÜV : 11842

Approvals are based on factory location. Please contact ESAB for more information.

<b>Alloy Type</b>	Carbon-manganese steel
<b>Shielding Gas</b>	I1 (EN ISO 14175)

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
<b>EN Ar (I1)</b>			
As Welded	470 MPa	560 MPa	26 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
<b>EN Ar (I1)</b>		
As Welded	-30 °C	70 J
As Welded	-40 °C	60 J

Typical Wire Composition %		
C	Mn	Si
0.078	1.46	0.85

Typical Weld Metal Analysis %				
C	Mn	Si	S	P
0.05	1.4	0.8	0.015	0.015